

## QUALITY & RELIABILITY ENGINEERING

### FIT and MTTF Calculation Report

<b>PN Family Series</b>	<b>TSUP5M45SH</b>
<b>Part Description</b>	5A, 45V Trench Schottky Rectifier
<b>Package Type</b>	SMPC4.6U

#### Test Variables:

Stress Test	=	<b>HTRB</b>	
No. of failures	=	0	<b>units</b>
Sample Size	=	77	<b>units</b>
Test Duration	=	1000	<b>hours</b>
Total device hours	=	77000	<b>hours</b>
Accelerated Temp (Ta)	=	175	<b>° C</b>
Operating Temp (Tu)	=	55	<b>° C</b>
Activation Energy (Ea)	=	0.7	<b>eV</b>
Confidence Level	=	90	<b>%</b>
Boltzmann's Constant (k)	=	8.617E-05	<b>eV / °K</b>

#### Calculations:

Chi squared value	=	<b>4.6051702</b>	@ 90% Confidence Level
Failure Rate ( <i>@accelerated condition</i> )	=	$\frac{(\text{Chi squared value})}{2 * (\text{Sample Size}) * (\text{Test Duration})}$	
	=	<b>29903.70</b>	<b>FIT</b>
Acceleration Factor, AF	=	$e^{(Ea/k)(1/Tu - 1/Ta)}$	
	=	<b>760.4701686</b>	

#### Results:

<b>Failure Rate</b> ( <i>@operating condition</i> )	=	(Failure Rate <i>@accelerated condition</i> ) / (AF)	
	=	<b>39</b>	<b>FIT</b>
<b>Mean Time to Failure (MTTF)</b>	=	<b>25430636</b>	<b>hours</b>
	=	<b>2903</b>	<b>years</b>